

Lijian Composite Materials Co.,LTD.

www.fiberglass-mat.com-Sale@fiberglass-mat.com-Tel :+86-13776546919-Fax:+86-25-68923190

Fiber Glass Yarns

- Serials-1:Fiber Glass Single Yarns
- Serials-2:Fiber Glass Twist Yarns
- Serials-3:Texturized Fiber Glass Yarns



- Serials-1:Fiber Glass Single Yarns

Linear Density	Filament Diameter	Moisture	LOI	Package Weight	Sizing
Tex	μm	%	%	kg	
68	11-13	≤0.5	0.6±0.2	1-5	Silane
100	11-13	≤0.5	0.6±0.2	1-5	
130	11-13	≤0.5	0.6±0.2	1-5	
200	11-13	≤0.5	0.6±0.2	1-5	

- Serials-2:Fiber Glass Twist Yarns


Product Code	Filament Diameter	Twist	Package Weight	Sizing
	μm		kg	
EC6-12.5X2	6	S or Z ;35-120	0.5-2.0	Paraffinic
EC8-24X1	8	S or Z ;35-120	0.5-2.0	
EC8-24X2	8	S or Z ;35-120	0.5-2.0	
EC9-30X2	9	S or Z ;35-120	0.5-2.0	
EC9-30X6	9	S or Z ;35-120	0.5-2.0	
EC8-24X1	8	S or Z ;35-120	0.5-2.0	Silane
EC9-30X2	9	S or Z ;35-120	0.5-2.0	
EC9-30X3	9	S or Z ;35-120	0.5-2.0	

Lijian Composite Materials Co.,LTD.

www.fiberglass-mat.com-Sale@fiberglass-mat.com-Tel :+86-13776546919-Fax:+86-25-68923190

- Serials-3:Texturized Fiber Glass Yarns

product code	English code	Linear Density	Filament Dia.(μm)	LOI(%)
ET 7 550 / NT (FT)	ETE 9.0 / NT (FT)	550	7 \pm 2	1.0 \pm 0.20
ET 9 420 / NT (FT)	ETG 11.8/ NT (FT)	420	9 \pm 2	0.90 \pm 0.20
ET 9 550 / NT (FT)	ETG 9.0/ NT (FT)	550	9 \pm 2	0.90 \pm 0.20
ET 9 827 / NT (FT)	ETG 6.0/ NT (FT)	827	9 \pm 2	0.90 \pm 0.20
ET 9 1160 / NT (FT)	ETG 4.3/ NT (FT)	1160	9 \pm 2	0.90 \pm 0.20
ET 9 1250 / NT (FT)	ETG 4.0/ NT (FT)	1250	9 \pm 2	0.90 \pm 0.20
ET 9 1300 / NT (FT)	ETG 3.8/ NT (FT)	1300	9 \pm 2	0.90 \pm 0.20
ET 9 1400 / NT (FT)	ETG 3.5/ NT (FT)	1400	9 \pm 2	0.90 \pm 0.20
ET 9 1835 / NT (FT)	ETG 2.7/ NT (FT)	1835	9 \pm 2	0.90 \pm 0.20
ET 9 2835 / NT (FT)	ETG 1.75/ NT (FT)	2835	9 \pm 2	0.90 \pm 0.20
ET 13 4400 /NT(FT)	ETK1.1/ NT (FT)	4400	13 \pm 2	0.5 \pm 0.20
ET 14 2200 /NT(FT)	ETK2.25/ NT (FT)	2200	14 \pm 2	0.5 \pm 0.20
ET 17 3500 /NT(FT)	ETK1.4/ NT (FT)	3500	17 \pm 2	0.5 \pm 0.20



Important Notice

Loading(uploading)-Please do not drag and drop

Please place in dry and shade

Please do not open package before use

Nanjing Lijian Composite Materials Co.,LTD.

Tel:0086-25-68923190 0086-13776546919

Fax:0086-25-68923190

Web:www.fiberglass-mat.com

E-mail:Sales@fiberglass-mat.com